



quality.always

MITASU OIL CORPORATION

1-2-9, Nishi Shimbashi, Minato-Ku, Tokyo, 105-0003, Japan
Tel: +81-3-5532-8187. Fax: +81-3-5532-8188
E-mail: info@mitasuoil.co.jp

MJ-103. MITASU GOLD PAO SN OW-30 ILSAC GF-5 100% Synthetic



1L



4L



20L



200L

MITASU GOLD PAO SN OW-30 ILSAC GF-5 100% Synthetic is a fully synthetic resource conserving motor oil, blended from synthetic base Group IV PAO (Poly-Alpha-Olefin) and Group III and meets the new GF-5 standard, set by the International Lubricants Standardization and Approval Committee (ILSAC). The newest ZDDP anti-wear additive package delivers the latest development in lubricating technology to maximize protection and cleanliness for the newest gasoline-fuelled engines.

APPLICATION

MITASU GOLD PAO SN OW-30 ILSAC GF-5 100% Synthetic has been designed for modern cars gasoline engines, operating under heavy duty load and exceeds the most demanding requirements for the latest engine emission control and fuel efficiency. It provides protection from oxidation. It has been designed for all-season use.

SPECIFICATIONS / APPROVALS

- API SN
- ILSAC GF-5
- FIAT 9.55535-GS1



APPLICATION BENEFITS

All-season MITASU GOLD PAO SN OW-30 ILSAC GF-5 100% Synthetic provides:

- Product's properties stability due to use of Poly-Alpha-Olefin Group base oil
- Fuel economy
- Maximum engine cleanliness
- Seal protection
- Extended service life
- Easy cold start at as low as -45°C

The ZDDP anti-wear additive package deposits much less phosphorous on the face of the catalyst, significantly reducing the poisoning of the catalyst system.

The latest technologies of MITASU OIL CORPORATION, Japan and the most advanced ILSAC GF-5 standard enable MITASU GOLD PAO SN OW-30 ILSAC GF-5 100% Synthetic to exceed the requirements of such car manufacturers as TOYOTA, HONDA, NISSAN, DAIHATSU, VW, BMW, VOLVO, OPEL, FORD and others.

TECHNICAL CHARACTERISTICS

Technical property	Method	Result
SAE viscosity grade	SAE J300	OW-30
Density at 15°C	ASTM D-4052	0,8442
Flash point, °C	ASTM D-92	219
TBN (mg KOH/g)	ASTM D-2896	7,00
Pour point, °C	ASTM D-97	-42
Colour	ASTM D-1500	<2,5
Viscosity index	ASTM D-2270	177
Kinematic viscosity at 40°C (cSt)	ASTM D-445	57,22
Kinematic viscosity at 100°C (cSt)	ASTM D-445	10,56

Due to continual product research and development, the information contained herein is subject to change without notification.